

Short Communication

SMART Tubing Presents an Increased Risk of Disconnection During Extracorporeal Circulation

Ross Newling, MSc, CCP; Richard Morris, MB, BS, FANZCA

Perfusion Department, St. George Hospital, Sydney, Australia

Presented at the 43rd International Conference of the American Society of Extra-Corporeal Technology, New Orleans, Louisiana, March 3–6, 2005

Abstract: A number of products exhibiting biocompatible features have been developed for use in extracorporeal blood circuits during cardiopulmonary bypass procedures. While attention has been focused on biocompatibility features of the blood-circuit interface, a number of issues applicable in clinical use of these circuits have arisen. Surface Modifying Additive Technology (SMART; Cobe Cardiovascular, Arvada, CO) is one such technology. In this product, the structure of normal polyvinylchloride (PVC) tubing is altered through the blending of two copolymers to give a more biocompatible blood to plastic interface. In this study, we examined the in vitro mechanical ability of

random samples ($n = 10$) of SMART and standard PVC tubing to withstand axial tension when the tubing was placed over a single barb of a connector. The tension required to remove the SMART tubing from the connector (83.3 ± 7.3 [SD] N), was significantly less than standard PVC tubing (115.6 ± 15.9 N; $p < .0001$, unpaired t test). The SMART tubing exhibited a 28% reduction in tubing to connector adhesion, which may have a significant effect on extracorporeal circuit disconnection and overall patient safety. **Keywords:** cardiopulmonary bypass, biocompatibility, surface modification, perfusion circuitry, accident prevention. *JECT. 2005;37:400–401*

Over recent years, the medical technology and plastics industries have developed improved biocompatible products to reduce the deleterious effects of blood contact with nonendothelial surfaces. Surface Modifying Additive Technology (SMART; Cobe Cardiovascular, Arvada, CO) is one such technology designed to minimize platelet activation caused by synthetic surfaces and thereby lessen the effects of blood interaction (1–3). SMART tubing is produced by copolymer blending of polycaprolactone and polysiloxane with base polyvinylchloride (PVC) (4,5). These copolymers form a triblock compound that migrates to the surface during manufacturing. Microdomains of alternating positive and negative charges are created along the surface of the tubing, rendering the surface hydro-

philic. This treatment also makes the tubing feel more slippery compared with standard PVC tubing. While it seems to slide onto barbed tubing connectors more readily, it may also slide off with important and dramatic consequences. There has been a recent incident reported where the arterial line disconnected from the arterial filter during cardiopulmonary bypass, even though cable ties had been used to secure the tubing (6). A similar disconnection at our institution, although this time on the low-pressure side of the circuit, prompted the current study.

MATERIALS AND METHODS

Random samples ($n = 10$), of 40-mm lengths of SMART tubing (0.372×0.094 in) and standard cardiac PVC tubing and were obtained from Cobe Cardiovascular. The tubing, at room temperature, was carefully placed on one end of a 0.372-in Cobe connector held securely in a 4-in engineers vice, so that the end of the tubing was uniformly just past the first barb of the connector. The free end of the tubing was attached to a spring balance

Address correspondence to: R. Newling, MSc, CCP, Perfusion Department, Operating Theatre Suite, 2nd Floor, Clinical Services Building, St. George Hospital, Gray St., Kogarah, New South Wales 2217, Australia. E-mail: newlingr@sesahs.nsw.gov.au

The senior author has stated that authors have reported no material, financial or other relationship with any healthcare-related business or other entity whose products or services are discussed in this paper.

with a second connector. Increasing axial tension was uniformly applied to the end of the spring balance until the tubing came off the vice-mounted connector. This permitted a comparison of the force required to detach each type of tubing.

RESULTS

The tension required to remove the SMART tubing from the connector (83.3 ± 7.3 [SD] N) was significantly less than standard PVC tubing (115.6 ± 15.9 N; $p < .0001$, unpaired t test). This means that 28% less force was required to detach the new SMART tubing compared with standard PVC tubing.

DISCUSSION

While SMART tubing is reported to have important blood-handling capabilities, there has been at least one report of tubing disconnection while being used with cardiopulmonary bypass (6).

This simple experiment showed that tubing-to-connector adhesion is lower for SMART tubing. This may

be of vital importance to perfusionists in terms of how extracorporeal circuits are assembled. We therefore recommend ensuring that the tubing is pushed fully onto barbed connectors and appropriately positioned, and tensioned cable ties are applied to both high- and low-pressure sections of the extracorporeal circuit.

REFERENCES

1. Gu YJ, Boonstra PW, Rijnsburger AA, Haan J, van Oeveren W. Cardiopulmonary bypass circuit treated with surface-modifying additives: A clinical evaluation of blood compatibility. *Ann Thorac Surg.* 1998;65:1342-7.
2. Rubens FD, Labow RS, Lavallee GR, et al. Hematologic evaluation of cardiopulmonary bypass circuits prepared with a novel block copolymer. *Ann Thorac Surg.* 1999;67:689-98.
3. Defraigne J-O, Pincemail J, Dekoster G, et al. SMA circuits reduce platelet consumption and platelet factor release during cardiac surgery. *Ann Thorac Surg.* 2000;70:2075-81.
4. Lovinger AJ, Han BJ, Padden FJ Jr, Mirau PA. Morphology and properties of polycaprolactone-poly(dimethyl siloxane)-polycaprolactone triblock copolymers. *J Polymer Sci.* 1993;31:115-23.
5. Tsai C-C, Deppisch RM, Forrestal LJ, et al. Surface modifying additives for improved device-blood compatibility. *ASAIO J.* 1994;40:M619-24.
6. Anon. Perfusion incident reporting system (PIRS). *ASCVP Gazette.* 2004;5:31-2.